

INSPECTION CERTIFICATE AS PER EN 10204-3.1

CUSTOMER : LLC ALFA GLOBAL-RUSSIA	 An ISO 9001, ISO 14001 & BS OHSAS 18001 Certified Company	MTR NO. / ISSUE DATE	EXP-473/15.12.2022
		BATCH NO.	S-1747
INVOICE NO. / P.O. NO. : EXP/22-23/624 DT-15.12.2022/SSIL/EXP/PI/22-23/398 DT-06.10.2022		GRADE	ER 316LSi
		SUPPLY CONDITION	STAINLESS STEEL SAW WELDING WIRE
		SURFACE FINISH	BRIGHT DRAWN, BRIGHT FINISH
		BRAND NAME	AG ER 316Lsi

CHEMICAL COMPOSITION OF WIRE :-

SR. NO.	DIAMETER (mm)	NUMBER OF SPOOLS	WEIGHT (KGS)	HEAT NO SPECIFIED	%C	%Mn	%Si	%S	%P	%Cr	%Ni	%Cu	%Mo	%N2
ELEMENTS %					MIN	-	1.00	0.65	-	-	18.00	11.00	-	2.00
					MAX	0.030	2.50	1.00	0.030	0.030	20.00	14.00	0.75	3.00
1	2.40 (K415/25KGS)	28	700.00	CH-17789	0.026	1.80	0.78	0.006	0.028	18.23	11.15	0.36	2.060	0.0690

MECHANICAL PROPERTIES OF ALL WELD METAL:-

SL. NO.	TENSILE STRENGTH	0.2% PROOF STRESS	ELONGATION %	REDUCTION OF AREA %	HARDNESS (BHN)	FERRITE NO (FN) (WRC-1992)	INCLUSION RATING				
							A	A	A	A	A
	(N/mm ²)	(N/mm ²)	Lo=100	-	-	-	THICK THIN	THICK THIN	THICK THIN	THICK THIN	THICK THIN
1	624	466	36	72	168	5	-	-	-	-	-

SPECIFICATION :-

TENSILE STRENGTH	AS PER AWS A5.9/A5.9 M : 2021
DIAMETER TOLERANCE	AS PER AWS A5.9/A5.9 M : 2021
% ELONGATION	STANDARD
MATERIAL SPECIFICATION	MATERIAL CONFORMS TO AWS A5.9/A5.9 M : 2021
IGC TEST AS PER ASTM A262 PRACTICE "E"	SATISFACTORY

MATERIAL IS FREE FROM MERCURY CONTAMINATION . FREE FROM WELD AND WELD REPAIRS .
 RADIOACTIVITY TEST : WE CONFIRM THE MATERIAL HAS BEEN TESTED AND FOUND TO BE FREE FROM RADIOACTIVE CONTAMINATION.



WE HEREBY CERTIFY THAT THE MATERIAL DESCRIBED ABOVE HAS BEEN TESTED AND COMPLIES WITH THE TERMS OF ORDER / CONTRACT. AUTHORIZED SIGNATORY